



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 262 450 A1**

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
04.12.2002 Bulletin 2002/49

(21) Application number: 02011603.4

(22) Date of filing: 28.05.2002

(51) Int Cl.7: **C01B 13/14**, C01G 23/00,
C01G 49/00, C30B 11/00,
H01F 1/34, H01F 1/37,
H01L 23/66, H01G 4/12,
H01F 5/00

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 31.05.2001 JP 2001165931

(71) Applicant: TDK Corporation
Chuo-ku, Tokyo 103-8272 (JP)

(72) Inventors:
• Takaya, Minoru
Chuo-ku, Tokyo 103-8272 (JP)

• Akachi, Yoshiaki
Chuo-ku, Tokyo 103-8272 (JP)
• Uematsu, Hiroyuki
Chuo-ku, Tokyo 103-8272 (JP)
• Kobuke, Hisashi
Chuo-ku, Tokyo 103-8272 (JP)

(74) Representative: HOFFMANN - EITLE
Patent- und Rechtsanwälte
Arabellastrasse 4
81925 München (DE)

(54) **Method for manufacturing single crystal ceramic powder, and single crystal ceramic powder, composite material, and electronic element**

(57) A method for manufacturing single crystal ceramic powder is provided. The method includes a powder supply step for supplying powder consisting essentially of ceramic ingredients to a heat treatment area with a carrier gas, a heat treatment step for heating the powder supplied to the heat treatment area at temperatures required for melting of the powder to form a product, and

a cooling step for cooling the product obtained in the heat treatment step to form single crystal ceramic powder. The method provides single crystal ceramic powder consisting of particles with a very small particle size and a sphericity being 0.9 or higher.

EP 1 262 450 A1